

**AMENDMENTS TO THE CLAIMS**

**Please replace the claims with the following rewritten set of claims:**

1. (Currently amended) A silver halide photographic light-sensitive material ~~having for~~ forming a silver image, comprising:  
at least one silver halide emulsion layer on a side of a support,  
at least one nucleating agent on the side having the emulsion layer, and  
wherein the support contains a filler treated with an organic onium ion.
2. (Original) The silver halide photographic light-sensitive material according to claim 1, wherein the filler has an aspect ratio of 50 to 10000.
3. (Original) The silver halide photographic light-sensitive material according to claim 1, wherein the filler has a thickness of 0.5 to 5 nm.
4. (Original) The silver halide photographic light-sensitive material according to claim 1, wherein the filler has an average particle size of 25 to 10000 nm.
5. (Canceled)
6. (Currently amended) The silver halide photographic light-sensitive material according to claim 5, 1, wherein the filler is a clay compound treated with an organic onium ~~ions~~ ion.
7. (Currently amended) The silver halide photographic light-sensitive material according to claim 6, wherein the filler is a smectite group clay compound treated with an organic onium ~~ions~~ ion.
8. (Currently amended) The silver halide photographic light-sensitive material according to claim 5, 1, wherein the filler is a swellable mineral treated with an organic onium ~~ions~~ ion.
9. (Currently amended) The silver halide photographic light-sensitive material according

to claim 8, wherein the filler is swellable mica treated with an organic onium ~~ions~~ ion.

10. (Currently amended) The silver halide photographic light-sensitive material according to claim 8, wherein the filler is swellable vermiculite treated with an organic onium ~~ions~~ ion.

11. (Original) The silver halide photographic light-sensitive material according to claim 1, which shows a gamma of 4.0 or more for the optical density range of 0.1 to 1.5 on a characteristic curve drawn in orthogonal coordinates of common logarithm of light exposure (x-axis) and optical density (y-axis) using equal unit lengths for the both axes.

12. (Currently amended) A silver halide photographic light-sensitive material ~~having~~ for forming a silver image, comprising:

at least one silver halide emulsion layer on a support and a back layer on the side of the support opposite to the side having the emulsion layer, ~~which has~~

at least one nucleating agent on the side having the emulsion layer, and

an undercoat layer containing a clay compound coated with an organic substance between the support and the emulsion layer or between the support and the back layer.

13. (Original) The silver halide photographic light-sensitive material according to claim 12, wherein the clay compound coated with an organic substance has an aspect ratio of 50 to 10000.

14. (Original) The silver halide photographic light-sensitive material according to claim 12, wherein the clay compound coated with an organic substance has a thickness of 0.5 to 5 nm.

15. (Currently amended) The silver halide photographic light-sensitive material according to claim 12, wherein the clay compound coated with an organic substance is a layered silicate compound treated with an organic onium ~~ions~~ ion.

16. (Currently amended) The silver halide photographic light-sensitive material

according to claim 15, wherein the clay compound coated with an organic substance is a smectite group clay compound treated with an organic onium ~~ions~~ ion.

17. (Currently amended) The silver halide photographic light-sensitive material according to claim 15, wherein the clay compound coated with an organic substance is swellable mica treated with an organic onium ~~ions~~ ion.

18. (Currently amended) The silver halide photographic light-sensitive material according to claim 15, wherein the clay compound coated with an organic substance is swellable vermiculite treated with an organic onium ~~ions~~ ions.

19. (Original) The silver halide photographic light-sensitive material according to claim 12, which has undercoat layers containing a clay compound coated with an organic substance between the support and the emulsion layer and between the support and the back layer.

20. (Original) The silver halide photographic light-sensitive material according to claim 12, which shows a gamma of 4.0 or more for the optical density range of 0.1 to 1.5 on a characteristic curve drawn in orthogonal coordinates of common logarithm of light exposure (x-axis) and optical density (y-axis) using equal unit lengths for the both axes.

21. (New) A silver halide photographic light-sensitive material having a property of forming a silver image through development by a developer having a pH of 9.0 to 11.0, wherein the silver halide photographic light-sensitive material comprises at least one silver halide emulsion layer on a support, and the support comprises a filler.

22. (New) A silver halide photographic light-sensitive material comprising at least one silver halide emulsion layer on a support, wherein the support comprises a filler treated with an alkylamine ion or an ammonium ion having both of an alkyl group and a glycol chain, or a filler treated with a phosphonium ion, a sulfonium ion or an onium ion derived from a heteroaromatic ring.

23. (New) A silver halide photographic light-sensitive material for forming a silver image comprising:

- at least one silver halide emulsion layer on a support, and
- at least one nucleating agent on the side having the emulsion layer;
- wherein the support comprises a polyester comprising a filler treated with an organic onium ion.

24. (New) A silver halide photographic light-sensitive material comprising at least one silver halide emulsion layer on a support,

- wherein the support comprises a filler, and wherein
- the support has a Young's modulus of 4400 to 15000 MPa in the portion containing the filler .

25. (New) A silver halide photographic light-sensitive material having a property of forming a silver image through development by a developer having a pH of 9.0 to 11.0,

- wherein the silver halide photographic light-sensitive material comprises:

- at least one silver halide emulsion layer on a support and a back layer on the side of the support opposite to the side having the emulsion layer, and

- an undercoat layer comprising a clay compound coated with an organic substance between the support and the emulsion layer or between the support and the back layer.

26. (New) A silver halide photographic light-sensitive material having a property of forming a silver image through development by a developer having a pH of 9.0 to 11.0,

- wherein the silver halide photographic light-sensitive material comprises:

- at least one silver halide emulsion layer on a support and a back layer on the side of the support opposite to the side having the emulsion layer,

- at least one nucleating agent on the side having the emulsion layer,

- an undercoat layer comprising a clay compound coated with an organic substance between the support; and

- wherein the support is free from fillers.

27. (New) A silver halide photographic light-sensitive material comprising:  
at least one silver halide emulsion layer on a support and  
at least one undercoat layer and a back layer on the side of the support opposite to the side having the emulsion layer;

wherein at least one undercoat layer comprises a clay compound coated with an organic substance between the support and the emulsion layer or between the support and the back layer, and

wherein the support has a Young's modulus of 4400 to 15000 MPa in a portion containing a filler.

28. (New) A silver halide photographic light-sensitive material comprising:  
at least one silver halide emulsion layer on a support,  
and at least one undercoat layer and a back layer on the side of the support opposite to the side having the emulsion layer;

wherein an undercoat layer is formed by coating between the support and the emulsion layer or between the support and the back layer, and

wherein the undercoat layer comprises a clay compound coated with an organic substance and at least one compound selected from the group consisting of polyester resin, polyamidoimide resin, polyurethane resin, vinyl chloride type resin, vinylidene chloride resin, phenol resin, epoxy resin, urea resin, melamine resin, formaldehyde resin, silicone resin, starch, denatured starch compound, alginic acid compound, casein, pullulan, dextran, chitin, chitosan, rubber latex, gum arabic, gumweed, natural gum, dextrin, denatured cellulosic resin, polyvinyl alcohol type resin, polyacrylic acid type resin, polyvinylpyrrolidone, polyethyleneimine, polyvinyl ether, polymaleate copolymer, polyacrylamide and alkyd resin.